

Stratocell[®] E Plus

Closed cell Polyethylene foam, CFC and HCFC free.

<u>PROPERTIES</u>	TEST METHOD	<u>UNIT</u>	<u>VALUE</u>
TENSILE STRENGTH Extrusion direction Cross direction	DIN 53571	N/mm ²	0,741 0,690
ELONGATION AT BREAK Extrusion direction Cross direction	DIN 53571	%	80 75
COMPRESSION STRENGTH 25 % (4th compression) 50 % (4th compression) 70 % (4th compression)	DIN 53577	N/mm²	0,024 0,081 0,200
THERMAL STABILITY (24h at 70° C)	ASTM D-3575-S	%	<0,5
CELL SIZE	BS 4443/1 Met.4	Cells/25 mm	≥ 21
WATER ABSORPTION (after 24 hours)	DIN 53428	Vol %	1,19

The information provided in this data sheet is in good faith.

No liability is, however, accepted for errors and omission and in no circumstances shall Sealed Air be liable in damages for loss or injury arising directly or as a consequence of the publication of this data sheet.